

Commercial Product Data Sheet

Product Description

Irex HT is a high performance, heavy duty base sheet or base ply designed for use with Veral and other torchable roof membrane systems. Irex HT consists of a fiberglass scrim/fiberglass mat composite impregnated and coated with a specially formulated, high quality, oxidized asphalt.

Product Uses

Irex HT is used as a ply sheet or base sheet depending on specification requirements for Siplast Veral and other Siplast Roof Systems. Irex HT is specifically designed for high tensile requirements and for use in conjunction with Siplast Veral Systems requiring extended warranties. Irex HT is lapped 3 inches (7.6 cm) side and end when applied in approved Type IV asphalt or by torching. In nailable applications, Irex HT is lapped 4 inches (10.2 cm) side and end, and is mechanically fastened according to Siplast requirements. Contact Siplast for specific approval on other product uses.

Product Approvals

Irex HT is approved by FM Approvals (FM Standard 4470) for use in Veral Class 1 insulated steel roof deck constructions and insulated and non-insulated concrete roof deck constructions, subject to FM conditions and limitations.

Irex HT has been classified by Underwriters Laboratories as a UL Rated G2 Base Sheet. Irex HT is approved by Underwriters Laboratories for use in cUL_{us} Classified Siplast Veral Roof Systems. Veral has been classified by Underwriters Laboratories as a Class A roofing system over non-combustible, insulated non-combustible, combustible, and insulated combustible decks.

Siplast Roof Systems also have received the approval of many regional and local authorities. Please contact Siplast for specific information as required.

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at www.Siplast.com.

COMMERCIAL PRODUCT INFORMATION

Unit:	Roll		
Coverage:	1.0 Square	(9.3 m ²)	
Coverage Weight Per Square:	Min: 85 lb	(4.1 kg/m ²)	
Roll Length:	Min: 34 ft	(10.36 m)	
Roll Width:	Avg: 3.28 ft	(1.00 m)	
Thickness:	Avg: 110 mils	(2.8 mm)	
	Min: 106 mils	(2.7 mm)	
Selvage Width:	N/A		
Selvage Surfacing:	N/A		
Top Surfacing:	Silica Parting Agent		
Back Surfacing:	Silica Parting Agent		

Lines: Two laying lines are placed 3 in (7.6 cm) and 4 in (10.2 cm) from each edge of the material. The line color for this material is green.

Packaging: Rolls are wound onto a compressed paper tube. The rolls are placed upright on pallets cushioned with corrugated cardboard and are adhered with adhesive at the labels. The top of the palleted rolls is covered with foiled Kraft paper. The palleted material is protected by a heat shrink polyethylene shroud.

Pallet: 41 in X 48 in (104 cm X 122 cm) wooden pallet
Number Rolls Per Pallet: 25
Number Pallets Per Truckload: 18
Minimum Roll Weight: 85 lb (38.6 kg)

Storage and Handling: All Siplast roll roofing products should be stored on end on a clean flat surface. Care should be taken that rolls are not dropped on ends or edges and are not stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing should be stored in a dry place, out of direct exposure to the elements, and should not be double stacked. Material should be handled in such a manner as to ensure that it remains dry prior to and during installation.

IREX HT

Physical and Mechanical Properties

Property (as Manufactured)	Values/Units	Test Method
Thickness (minimum)	106 mils (2.7 mm)	ASTM D 5147 section 5
Thickness (average)	110 mils (2.8 mm)	ASTM D 5147 section 5
¹ Peak Load @ 73°F (average)	80 lbf/inch (14.1 kN/m)	ASTM D 5147 section 6
¹ Peak Load @ 0°F (average)	150 lbf/inch (26.5 kN/m)	ASTM D 5147 section 6
¹ Elongation @ Peak Load, 73°F (average)	4%	ASTM D 5147 section 6
¹ Elongation @ Peak Load, 0°F (average)	4%	ASTM D 5147 section 6
¹ Tear Strength (average)	120 lbf (0.54 kN)	ASTM D 5147 section 7
Water Absorption (maximum)	1%	ASTM D 5147 section 9
Dimensional Stability (maximum)	0.1%	ASTM D 5147 section 10
High Temperature Stability (minimum)	200°F (93°C)	ASTM D 5147 section 15
Coating Thickness - Back Surface	≥ 40 mils (1 mm)	ASTM D 5147 section 16

1. The value reported is the lower of either MD or XD.