

# PA-1130 ASPHALT EMULSION PRIMER

## Commercial Product Data Sheet

### **Product Description**

PA-1130 Asphalt Emulsion Primer is a general purpose asphalt-based emulsion primer designed as a primary coating for metal and masonry surfaces prior to application of Siplast Roofing and Flashing Systems.

### **Product Uses**

PA-1130 Asphalt Emulsion Primer is applied to all metal flanges and concrete and masonry surfaces; the primer should be allowed to dry thoroughly prior to application of Siplast Roofing and Flashing Systems. PA-1130 can be applied by roller, brush, or spray. PA-1130 may not be diluted.

### **Temperature Considerations and Limitations**

Do not apply PA-1130 Asphalt Emulsion Primer when surface or ambient temperature is below 50°F (10°C) or when relative humidity is above 90%. Cool temperatures and high humidity retard curing. PA-1130 should only be applied when weather conditions will permit drying before rain, dew, or freezing temperatures occur.

### **Product Approvals**

PA-1130 Asphalt Primer meets all regional and national VOC regulations.

*Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at [www.Siplast.com](http://www.Siplast.com).*

### **COMMERCIAL PRODUCT INFORMATION**

Maximum VOC Content: 10 g/l or less

Unit: 5-Gallon Pail  
4.7 gallons (17.8 liters) net content

Coverage: Coverage is dependent on the condition of the surface receiving the primer. The coverage ranges from 100 square feet per gallon on very rough, porous surfaces to 400 square feet per gallon on smooth, low-absorptive surfaces.

Flash Point, Cleveland Open Cup: 400°F (204°C)

Shelf Life: 1 year

Packaging: The pails are stacked three high on pallets and stretch wrapped.

Pallet: 36 in X 48 in (91 cm X 122 cm) wooden pallet.

Number Pails Per Pallet: 36

Number Pallets Per Truckload: 42

Weight Per Pail: 45 lb (20.4 kg)

Shipping Classifications: White Label (combustible)

Storage and Handling: All containers of PA-1130 Asphalt Primer should be stored upright on a clean, flat surface at temperatures between 40°F (4°C) and 100°F (38°C). Care should be taken that containers are not dropped and container seals are not broken prior to use. All containers should be stored in a dry place, out of direct exposure to the elements, and should be kept away from excessive heat, fire or open flames. Do not allow containers of PA-1130 Asphalt Emulsion Primer to freeze.

Rev 10/07