

# PARADIENE 20 P



## Commercial Product Data Sheet

### Product Description

Paradiene 20 P is a high performance modified bitumen base ply specifically designed for use in Parapro roof membrane systems. Paradiene 20 P consists of a lightweight random fibrous glass mat impregnated and coated with high quality styrene-butadiene-styrene (SBS) modified bitumen. The unique top surface is factory coated with a proprietary Syntan acrylic coating.

### Product Uses

Paradiene 20 P is the first ply of Siplast Paradiene 20 P/Parapro Roof Systems, and is lapped 3 inches (7.6 cm) side and end. Paradiene 20 P can be applied in approved Type IV asphalt or SFT Adhesive. Contact Siplast for specific approval on other product uses.

### Product Approvals

Paradiene 20 P is approved by FM Approvals for use in Siplast Paradiene 20 P/Parapro Class 1 insulated steel roof deck constructions and insulated and non-insulated concrete roof deck constructions, subject to FM conditions and limitations.

Paradiene 20 P is listed by Underwriters Laboratories for use in cUL<sub>us</sub> Classified Siplast Paradiene 20 P/Parapro Roof Systems.

Paradiene 20 P meets or exceeds the requirements of ASTM D 6163 Type I, Grade S, for SBS-modified bituminous sheet materials using glass fiber reinforcements.

Siplast Roof Systems also have received the approval of many regional and local authorities. Please contact Siplast for specific information as required.

*Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at [www.Siplast.com](http://www.Siplast.com).*

1. Syntan® is a registered trademark of Icopal.

### COMMERCIAL PRODUCT INFORMATION

Unit:	Roll	
Coverage:	1.5 Squares	(13.9 m <sup>2</sup> )
Coverage Weight Per Square:	Min: 59 lb	(2.9 kg/m <sup>2</sup> )
Roll Length:	Min: 50 ft	(15.24 m)
Roll Width:	Avg: 3.28 ft	(1.00 m)
Thickness:	Avg: 91 mils	(2.3 mm)
	Min: 87 mils	(2.2 mm)
Selvage Width:	N/A	
Selvage Surfacing:	N/A	
Top Surfacing:	Syntan® Acrylic Coating <sup>1</sup>	
Back Surfacing:	Silica Parting Agent	

Lines: A laying line is placed 3 in (76 mm) from each edge of the material. The line color for this material is blue.

Packaging: Rolls are wound onto a compressed paper tube. The rolls are placed upright on pallets cushioned with corrugated cardboard and are adhered with adhesive at the labels. The top of the palleted rolls is covered with foiled Kraft paper. The palleted material is protected by a heat shrink polyethylene shroud.

Pallet: 41 in X 48 in (104 cm X 122 cm) wooden pallet  
Number Rolls Per Pallet: 25  
Number Pallets Per Truckload: 18  
Minimum Roll Weight: 89 lb (40.4 kg)

Storage and Handling: All Siplast roll roofing products should be stored on end on a clean flat surface. Care should be taken that rolls are not dropped on ends or edges and are not stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing should be stored in a dry place, out of direct exposure to the elements, and should not be double stacked. Material should be handled in such a manner as to ensure that it remains dry prior to and during installation.

# PARADIENE 20 P

## Physical and Mechanical Properties

Property (as Manufactured)	Values/Units	Test Method
Thickness (minimum)	87 mils (2.2 mm)	ASTM D 5147 section 5
Thickness (average)	91 mils (2.3 mm)	ASTM D 5147 section 5
<sup>1</sup> Peak Load @ 73°F (average)	30 lbf/inch (5.3 kN/m)	ASTM D 5147 section 6
<sup>1</sup> Peak Load @ 0°F (average)	70 lbf/inch (12.3 kN/m)	ASTM D 5147 section 6
<sup>1</sup> Elongation @ Peak Load, 73°F (average)	3%	ASTM D 5147 section 6
<sup>1</sup> Elongation @ Peak Load, 0°F (average)	3%	ASTM D 5147 section 6
<sup>1</sup> Ultimate Elongation @ 73°F (average)	50%	ASTM D 5147 section 6
<sup>1</sup> Tear Strength (average)	40 lbf (0.18 kN)	ASTM D 5147 section 7
Water Absorption (maximum)	1%	ASTM D 5147 section 9
Dimensional Stability (maximum)	0.1%	ASTM D 5147 section 10
Low Temperature Flexibility (maximum)	-13°F (-25°C)	ASTM D 5147 section 11
High Temperature Stability (minimum)	250°F (121°C)	ASTM D 5147 section 15
Cyclic Fatigue	Paradiene 20 P, bonded to Parapro Roof Membrane, passes ASTM D 5849 both as-manufactured and after heat conditioning according to ASTM D5147.	

1. The value reported is the lower of either MD or XD.