

# PARADIENE 30 HT FR TG



## Commercial Product Data Sheet

### Product Description

Paradiene 30 HT FR TG is a high performance, torch grade modified bitumen finish ply designed for use in homogeneous multi-layer modified bitumen roof membrane systems. Paradiene 30 HT FR TG consists of a fiberglass scrim/fiberglass mat composite impregnated and coated with high quality styrene-butadiene-styrene (SBS) modified bitumen, and surfaced with ceramic granules. The back surface is coated with a high performance modified asphalt adhesive layer specifically formulated for torch applications. The adhesive layer is manufactured using a special process that embosses the surface with a grooved pattern to provide optimum burnoff of the plastic film and maximize application rates.

### Product Uses

Paradiene 30 HT FR TG is the finish ply of the Siplast Paradiene 20 TG/30 HT FR TG System, and is lapped 3 inches (7.6 cm) side and end. Siplast Paradiene 20 TG/30 HT FR TG Systems are torch applied to approved substrates. Contact Siplast for specific approval on product uses.

### Product Approvals

Paradiene 30 HT FR TG is approved by FM Approvals (FM Standard 4470) for use in Siplast Paradiene 20 TG/30 HT FR TG Class 1 insulated steel roof deck constructions and insulated and non-insulated concrete roof deck constructions, subject to FM conditions and limitations.

Paradiene 30 HT FR TG is approved by Underwriters Laboratories for use in  $c_{UL-us}$  Classified Siplast Paradiene 20 TG/30 HT FR TG Roof Systems. Siplast Paradiene 20 TG/30 HT FR TG has been classified by Underwriters Laboratories as a Class A roofing system over non-combustible, insulated non-combustible, insulated combustible decks, and as a Class B roofing system over combustible decks.

Paradiene 30 HT FR TG is approved by Underwriters Laboratories for use in  $c_{UL-us}$  Classified Siplast Paradiene 20 TG/30 HT FR TG Roof Systems. Siplast Paradiene 20 TG/30 HT FR TG Roof Systems have been classified as Class C roofing systems over combustible, non-combustible, and insulated combustible decks.

Paradiene 30 HT FR TG meets or exceeds the requirements of ASTM D 6163 Type II, Grade G, for SBS-modified bituminous sheet materials using glass fiber reinforcements.

Siplast Roof Systems also have received the approval of many regional and local authorities. Please contact Siplast for specific information as required.

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at [www.Siplast.com](http://www.Siplast.com).

### COMMERCIAL PRODUCT INFORMATION

Unit:	Roll		
Coverage:	0.75 Square	(7.0 m <sup>2</sup> )	
Coverage Weight Per Square:	Min:	112 lb	(5.4 kg/m <sup>2</sup> )
Roll Length:	Min:	25.25 ft	(7.70 m)
Roll Width:	Avg:	3.28 ft	(1.00 m)
Thickness:	Avg:	138 mils	(3.5 mm)
Thickness at Selvage:	Avg:	118 mils	(3.0 mm)
	Min:	114 mils	(2.9 mm)
Selvage Width:	Avg:	2.75 in	(70 mm)
Selvage Surfacing:	Release Tape		

Top Surfacing: No. 11 ceramic granules, standard color finishes are #93 Bone White and #65 Cinnamon Brown. Contact Siplast for other available colors.

Back Surfacing: Polyolefin Film

Lines: A laying line is placed 3 in (7.6 cm) from selvage edge of the material. The line color for this material is red.

Packaging: Rolls are wound onto a compressed paper tube. The rolls are placed upright on ends opposite the selvage on pallets cushioned with corrugated cardboard and are adhered with adhesive at the labels. The top of the palletted rolls is covered with foiled Kraft paper. The palletted material is protected by a heat shrink polyethylene shroud.

Pallet: 41 in X 48 in (104 cm X 122 cm) wooden pallet  
Number Rolls Per Pallet: 25  
Number Pallets Per Truckload: 18  
Minimum Roll Weight: 84 lb (38.1 kg)

Storage and Handling: All Siplast roll roofing products should be stored on end on a clean flat surface. Care should be taken that rolls are not dropped on ends or edges and are not stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing should be stored in a dry place, out of direct exposure to the elements, and should not be double stacked. Material should be handled in such a manner as to ensure that it remains dry prior to and during installation.

# PARADIENE 30 HT FR TG

## Physical and Mechanical Properties

Property (as Manufactured)	Values/Units	Test Method
Thickness (average)	138 mils (3.5 mm)	ASTM D 5147 section 5
<sup>1</sup> Thickness at selvage (minimum) (average)	114 mils (2.9 mm) 118 mils (3.0 mm)	ASTM D 5147 section 5
<sup>2</sup> Peak Load @ 73°F (average)	80 lbf/inch (14.1 kN/m)	ASTM D 5147 section 6
<sup>2</sup> Peak Load @ 0°F (average)	150 lbf/inch (26.5 kN/m)	ASTM D 5147 section 6
<sup>2</sup> Elongation @ Peak Load, 73°F (average)	3%	ASTM D 5147 section 6
<sup>2</sup> Elongation @ Peak Load, 0°F (average)	3%	ASTM D 5147 section 6
<sup>2</sup> Ultimate Elongation @ 73°F (average)	55%	ASTM D 5147 section 6
<sup>2</sup> Tear Strength (average)	120 lbf (0.54 kN)	ASTM D 5147 section 7
Water Absorption (maximum)	1%	ASTM D 5147 section 9
Dimensional Stability (maximum)	0.1%	ASTM D 5147 section 10
Low Temperature Flexibility (maximum)	-13°F (-25°C)	ASTM D 5147 section 11
Granule Embedment Max. avg. loss Max. individual loss	1.5 grams per sample 2.0 grams per sample	ASTM D 5147 section 14
High Temperature Stability (minimum)	250°F (121°C)	ASTM D 5147 section 15
Coating Thickness - Back Surface	≥ 40 mils (1 mm)	ASTM D 5147 section 16
Cyclic Fatigue	Paradiene 30 HT FR TG, bonded to an acceptable Paradiene 20 base ply with an approved method of attachment, passes ASTM D 5849 both as-manufactured and after heat conditioning according to ASTM D5147.	

1. Measured on the selvage edge excluding the granule surfacing.
2. The value reported is the lower of either MD or XD.