

PA-750 PROTECTION COURSE S



Commercial Product Data Sheet

Product Description

PA-750 Protection Course S is a lightly modified asphalt coated fiberglass sheet designed as a protection layer for use with PA-750 Hot-Applied Rubberized Waterproofing Systems. PA-750 Protection Course S consists of a lightweight random fibrous glass mat impregnated and coated with a modified blend of styrene-butadiene-styrene (SBS) and asphalt.

Product Uses

PA-750 Protection Course S is set in PA-750 Rubberized Asphalt over the completed rubberized asphalt membrane; edges are butted together.

Product Approvals

Siplast Roof Systems have received the approval of many regional and local authorities. Please contact Siplast for specific information as required.

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at www.Siplast.com.

Rev 5/17

COMMERCIAL PRODUCT INFORMATION

Unit:	Roll		
Coverage:	3 Squares	(27.9 m ²)	
Coverage Weight Per Square:	Min: 30 lb	(1.3 kg/m ²)	
Roll Length:	Min: 102.3 ft	(31.2 m)	
Roll Width:	Avg: 3.28 ft	(1.00 m)	
Thickness:	Avg: 47 mils	(1.2 mm)	
	Min: 39 mils	(1.0 mm)	
Top Surfacing:	Silica Parting Agent		
Back Surfacing:	Silica Parting Agent		

Lines: Two laying lines are placed 3 in (7.6 cm) and 13 5/8 in (34.6 cm) from each edge of the material. The line color for this material is blue.

Packaging: The palletted material is protected by a heat shrink polyethylene shroud.

Pallet: 41 in X 48 in (104 cm X 122 cm) wooden pallet
Number Rolls Per Pallet: 20
Number Pallets Per Truckload: 18
Minimum Roll Weight: 90 lb (40.8 kg)

Storage and Handling: All Siplast roll roofing products should be stored on end on a clean flat surface. Care should be taken that rolls are not dropped on ends or edges and are not stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing should be stored in a dry place, out of direct exposure to the elements, and should not be double stacked. Material should be handled in such a manner as to ensure that it remains dry prior to and during installation.