

# PRO COLOR FINISH RESIN



## Commercial Product Data Sheet

### Product Description

Pro Color Finish Resin is a color pigmented, high performance, multi-component, fast curing, flexible PMMA resin for use in Parapro Roof Membrane, Parapro Flashing, Terapro Waterproofing & Surfacing Systems, and Terapro VTS Systems.

### Product Uses

Pro Color Finish Resin is used as a finish layer for Terapro Flashings, and as the finish layer over Terapro and Terapro VTS Systems surfaced with Pro Natural Quartz, or Pro Texture Beads. Pro Color Finish is also used as an optional finish layer for Parapro Roof Membrane and Parapro Flashing Systems.

### Colors

Pro Color Finish Resin is supplied in the following standard colors: Terracotta - 8081, Beige - 1015, Beige - 1019, Gray - 7035, Gray - 7042, Gray - 7043, Gray - 7044, Gray - 520001, Teak - 8023, Green - 6002, Red - 311910, Brown - 8025, Patina - 61-0107. Contact Siplast for availability of other colors.

### Packaging

Pro Color Finish Resin is supplied in 10-kg (22-lb) resealable drums with locking rings.

### Coverage Rates

#### Parapro Roof and Flashing Membranes (no aggregate)

Minimum consumption: 0.046 kg/sf (0.5 kg/m<sup>2</sup>)

#### Parapro & Terapro Pro Natural Quartz-surfaced Systems

Minimum consumption: 0.06 kg/sf (0.65 kg/m<sup>2</sup>)

#### Terapro Pro Accent Chip-surfaced Systems and Terapro VTS

Systems: Minimum consumption: 0.07 kg/sf (0.75 kg/m<sup>2</sup>)

See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

### Application Conditions

Pro Color Finish Resin can be applied when the ambient and substrate temperature is between 32°F (0°C) and 95°F (35°C). Discontinue resin application when the ambient or substrate temperature is outside the ranges listed above. Provide adequate shade over the substrate area both prior to and during application as necessary to maintain substrate surface temperatures below 95° F (35° C).

### Storage

Product shelf life is 6 months from ship date. Shelf life will be reduced if product is stored at temperatures above 77°F (25°C). Store indoors in a closed container in a well-ventilated, cool, dry area away from heat, open fire, any ignition source, direct sunlight, oxidizing agents, strong acids, and strong alkalis. Do not store in temperatures below 32°F (0°C). Product may auto-polymerize at temperatures greater than 140°F (60°C). Materials stored on the job site during application should be kept on a pallet in a shaded, well-ventilated area. In unshaded areas, materials should be covered with a white, reflective tarp in a manner that allows air circulation beneath the tarp.

### Handling

Do not smoke. Keep away from open fire, flame or any ignition source. Vapors may form explosive mixtures with air. Avoid skin and eye contact with this material. Avoid breathing fumes. Do not eat, drink, or smoke in the application area. Consult the Safety Data Sheet (SDS) for additional information pertaining to this product.

### Personal Protection Equipment (PPE)

Workers must wear a long sleeved shirt with long pants and work boots. Workers must use only butyl rubber or nitrile gloves when mixing or applying this product. Safety goggles are required for eye protection.

Use local exhaust ventilation to maintain worker exposure below TLV. If the airborne concentration poses a health hazard, becomes irritating, or exceeds recommended limits, use a NIOSH approved respirator in accordance with OSHA Respirator Protection requirements under 29 CFR 1910.134. Specific type of respirator will depend of the airborne concentration. Filtering face piece or dust mask is not acceptable for use with this product if TLV filtering levels have been exceeded.

### Mixing & Catalyzing

If batch mixing, thoroughly mix the entire drum of resin for 2-3 minutes prior to pouring resin into a second container. Catalyze only the amount of resin that can be used within the anticipated pot life. Add pre-measured catalyst to the resin, stir for 2 minutes using a slow-speed mechanical agitator or mixing stick, and apply to the substrate. The amount of catalyst needed is based on the weight of the resin used, and varies with the ambient temperature as shown in the chart on the back of this sheet.

### Pot Life

Pro Color Finish Resin pot life is approximately 15 minutes at 68°F (20°C). Pot life will be reduced if the resin is at higher temperatures. Pot life can be maximized by storing product under controlled conditions and ensuring that the resin is at the low range of minimum storage temperature during/following the addition of catalyst and prior to application.

### Set (Cure) Times

Minimum set (cure) times noted below are approximate, and may vary. The information provided is based on laboratory conditions, and is intended for use as a guideline only. Actual set (cure) times should be established in the field, based on actual field conditions.

Rain Proof at 68°F (20°C): Approximately 30 minutes  
Ready for next coat at 68°F (20°C): Approximately 45 minutes  
Stress Resistant at 68°F (20°C): Approximately 2 hours

### Tool Cleaning

When work is interrupted or completed, tools must be thoroughly cleaned with Pro Prep before any catalyzed resin on the tools hardens.

Rev 5/2015

# PRO COLOR FINISH RESIN

## Pro Catalyst Mixing Chart

The amount of Pro Catalyst used with Pro Color Finish Resin varies from a minimum of 2% to 6% maximum by weight, depending upon the ambient temperatures as indicated in the following table:

Resin Quantity	2% Catalyst 59°F to 95°F (15°C to 35°C)				4% Catalyst 41°F to 59°F (5°C to 15°C)				6% Catalyst 32°F to 41°F (0°C to 5°C)			
	g	kg	Tblsp.	0.1-kg Bags	g	kg	Tblsp.	0.1-kg Bags	g	kg	Tblsp.	0.1-kg Bags
1.0 kg (1.0 liter)	20	.02	2	n/a	40	.04	4	n/a	60	.06	6	n/a
5.0 kg (5.0 liter)	100	0.1	10	1	200	0.2	20	2	300	0.3	30	3
10.0 kg (10.0 liter)	200	0.2	20	2	400	0.4	40	4	600	0.6	60	6

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at [www.Siplast.com](http://www.Siplast.com).