

PARADIENE 30 MW FR



Commercial Product Data Sheet

Product Description

Paradiene 30 MW FR is an ultra high tensile strength, modified bitumen finish ply designed for use in multi-layer modified bitumen roof membrane systems. Paradiene 30 MW FR consists of a special-woven fiberglass reinforcement impregnated and coated with high quality styrene-butadiene-styrene (SBS) modified bitumen, and surfaced with ceramic granules.

Paradiene 30 MW FR is available with Siplast RoofTag RFID roof asset technology on a Special-Made-To-Order basis. See RoofTag Commercial Product Data Sheet for more information.

Product Uses

Paradiene 30 MW FR is the finish ply of the Siplast Paradiene 20/30 MW FR System, and is lapped 3 inches (7.6 cm) side and end. Paradiene 30 MW FR is specifically designed for high tensile requirements. Paradiene 30 MW FR can be applied in approved Type IV asphalt, Siplast PA-311 Adhesives, or SFT Adhesive. Contact Siplast for specific approval on other product uses.

Product Approvals

Paradiene 30 MW FR is approved by FM Approvals (FM Standard 4470) for use in Siplast Paradiene 20/30 MW FR Class 1 insulated steel roof deck constructions and insulated and non-insulated concrete roof deck constructions, subject to FM conditions and limitations.

Paradiene 30 MW FR is classified by Underwriters Laboratories for use in cULus Classified Siplast Paradiene 20/30 MW FR Roof Systems. Siplast Paradiene 20/30 MW FR has been classified by Underwriters Laboratories as a Class A roofing system over non-combustible, insulated non-combustible, and insulated combustible decks, and as a Class B roofing system over combustible decks.

Paradiene 30 MW FR meets or exceeds the requirements of ASTM D 6163 Type III, Grade G, and CSA A123.23-15 Type A, Grade 1 for SBS-modified bituminous sheet materials using glass fiber reinforcements.

Siplast Roof Systems also have received approval of many regional and local authorities. Please contact Siplast for specific information as required.

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at www.Siplast.com.

COMMERCIAL PRODUCT INFORMATION

Unit:	Roll	
Coverage:	1.0 Square	(9.3 m ²)
Coverage Weight Per Square:	Min: 96 lb	(4.7 kg/m ²)
Roll Length:	Min: 33.5 ft	(10.21 m)
Roll Width:	Avg: 3.28 ft	(1.00 m)
Thickness:	Avg: 138 mils	(3.5 mm)
Thickness at Selvage:	Avg: 106 mils	(2.7 mm)
	Min: 102 mils	(2.6 mm)
Selvage Width:	Avg: 2.75 in	(7.0 cm)
Selvage Surfacing:	Silica parting agent	

Top Surfacing: No. 11 ceramic granules, standard color finish is #A-720 Bone White. Contact Siplast for other available colors.

Back Surfacing: Silica Parting Agent

Lines: A laying line is placed 3 in (7.6 cm) from selvage edge of the material. The line color for this material is red.

Packaging: Rolls are wound onto a compressed paper tube. The rolls are placed upright on ends opposite the selvage on pallets cushioned with corrugated cardboard and are adhered with adhesive at the labels. The top of the palletted rolls is covered with Kraft paper. The palletted material is protected by a heat shrink polyethylene shroud.

Pallet: 41 in X 48 in (104 cm X 122 cm) wooden pallet.
Number Rolls Per Pallet: 25
Number Pallets Per Truckload: 18
Minimum Roll Weight: 96 lb (43.5 kg)

Storage and Handling: All Siplast roll roofing products should be stored on end on a clean flat surface. Care should be taken that rolls are not dropped on ends or edges and are not stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing should be stored in a dry place, out of direct exposure to the elements, and should not be double stacked. Material should be handled in such a manner as to ensure that it remains dry prior to and during installation.

Rev 1/2018

PARADIENE 30 MW FR

Physical and Mechanical Properties

UNITED STATES TEST STANDARDS			CANADA TEST STANDARDS	
Property (as Manufactured)	Values/Units	Test Method	Property (as manufactured)	Test Method CSA A123.23-15 Values/Units
Thickness (average)	138 mils (3.5 mm)	ASTM D 5147 section 6	Thickness (average)	3.5 mm (138 mils)
¹ Thickness at selvage (minimum) (average)	102 mils (2.6 mm) 106 mils (2.7 mm)	ASTM D 5147 section 6	¹ Thickness at selvage (minimum) (average)	2.6 mm (102 mils) 2.7 mm (106 mils)
² Peak Load @ 73°F (23°C) (average)	500 lbf/inch (87.6 kN/m)	ASTM D 5147 section 7	² Peak Load @ 23°C (73°F) (average)	87.6 kN/m (500 lbf/inch)
Peak Load @ 0°F (-17°C) (average)	600 lbf/inch (105.1 kN/m)	ASTM D 5147 section 7	Peak Load @ -17°C (0°F) (average)	105.1 kN/m (600 lbf/inch)
² Elongation @ Peak Load, 73°F (23°C) (average)	7%	ASTM D 5147 section 7	² Elongation @ Peak Load, 23°C (73°F) (average)	7%
² Ultimate Elongation @ 73°F (23°C) (average)	8%	ASTM D 5147 section 7	² Ultimate Elongation @ 23°C (73°F) (average)	8%
² Tear Strength (average)	800 lbf 3.6 (kN)	ASTM D 5147 section 8	N/A	N/A
Water Absorption (maximum)	1%	ASTM D 5147 section 10	N/A	N/A
Dimensional Stability (maximum)	0.1%	ASTM D 5147 section 11	Dimensional Stability (maximum)	0.1%
Low Temperature Flexibility (maximum)	-15°F (-26°C)	ASTM D 5147 section 12	Low Temperature Flexibility (maximum)	-26°C (-15°F)
Granule Embedment Max. avg. loss Max. individual loss	1.5 grams per sample 2.0 grams per sample	ASTM D 5147 section 15	Granule Embedment Max. avg. loss Max. individual loss	1.5 grams per sample 2.0 grams per sample
Compound Stability (minimum)	250°F (121°C)	ASTM D 5147 section 16	Compound Stability (minimum)	121°C (250°F)
Cyclic Fatigue	Paradiene 30 MW FR, bonded to an acceptable Paradiene 20 base ply with an approved method of attachment, passes ASTM D 5849 both as-manufactured and after heat conditioning according to ASTM D 5147.		Mass Per Unit Area Minimum	4.7 kg/m ² (96 lb/sq)

1. Measured on the selvage edge excluding the granule surfacing.
2. The value reported is the lower of either MD or XD.