

PRO PASTE RESIN



Commercial Product Data Sheet

Product Description

Pro Paste Resin is a high performance multi-component, fast curing, PMMA resin paste.

Product Uses

Pro Paste Resin is used for remediation of depressions in substrate surfaces or other surface irregularities prior to application of a Parapro Roof Membrane System or Terapro Waterproofing and Surfacing System.

Color

Pro Paste Resin is supplied in a pebble gray color, #7032.

Packaging

Pro Paste Resin is supplied in 10-kg (22-lb) resealable drums with locking rings.

Application and Coverage Rates

Maximum thickness per lift: 5 mm (3/16 inch)
See Siplast Installer's Guides for specific applications.

Application Conditions

Pro Paste can be applied when the ambient temperature is between 32°F (0°C) and 95°F (35°C) and the substrate temperature is between 32°F (0°C) and 122°C (50°C). Discontinue resin application when the ambient or substrate temperature is outside the ranges listed above. Provide adequate shade over the substrate area both prior to and during application as necessary to maintain substrate surface temperatures below 122° F (50° C).

Storage

Product shelf life is 6 months from ship date. Shelf life will be reduced if product is stored at temperatures above 77°F (25°C). Store indoors in a closed container in a well-ventilated, cool, dry area away from heat, open fire, any ignition source, direct sunlight, oxidizing agents, strong acids, and strong alkalis. Do not store in temperatures below 32°F (0°C). Product may auto-polymerize at temperatures greater than 140°F (60°C). Materials stored on the job site during application should be kept on a pallet in a shaded, well-ventilated area. In unshaded areas, materials should be covered with a white, reflective tarp in a manner that allows air circulation underneath the tarp.

Mixing & Catalyzing

If batch mixing, thoroughly mix the entire drum of resin for 2-3 minutes prior to pouring resin into a second container. Catalyze only the amount of resin that can be used within the anticipated pot life. Use only Pro Catalyst Liquid to catalyze Pro Paste Resin. Add pre-measured liquid catalyst to the resin, stir for 2 minutes using a slow-speed mechanical agitator or mixing stick, and apply to the substrate. Pro Paste Resin is catalyzed only with Pro Catalyst Liquid. The amount of catalyst needed is based on the weight of the resin used, and varies with the ambient temperature as shown in the chart on the back of this sheet.

Pot Life

Pro Paste Resin pot life is approximately 15 minutes at 68°F (20°C). Pot life will be reduced if the resin is at higher temperatures. Pot life can be maximized by storing product under controlled conditions and ensuring that the resin is at the low range of minimum storage temperature during/following the addition of catalyst and prior to application.

Set (Cure) Times

Minimum set (cure) times noted below are approximate, and may vary. The information provided is based on laboratory conditions, and is intended for use as a guideline only. Actual set (cure) times should be established in the field, based on actual field conditions.

Rain Proof at 68°F (20°C): Approximately 30 minutes
Ready for Next Coat at 68°F (20°C): Approximately 60 minutes
Stress Resistant at 68°F (20°C): Approximately 3 hours

Tool Cleaning

When work is interrupted or completed, reusable tools must be thoroughly cleaned with Pro Prep or Pro Prep M before any catalyzed resin on the tools hardens.

Handling

Do not smoke. Keep away from open fire, flame or any ignition source. Vapors may form explosive mixtures with air. Avoid skin and eye contact with this material. Avoid breathing fumes. Do not eat, drink or smoke in the application area.

Personal Protection Equipment (PPE)

Workers must wear a long sleeved shirt with long pants and work boots. Workers must use only butyl rubber or nitrile gloves when mixing or applying this product. Safety goggles are required for eye protection.

Use local exhaust ventilation to maintain worker exposure below TLV. If the airborne concentration poses a health hazard, becomes irritating or exceeds recommended limits, use a NIOSH approved respirator in accordance with OSHA Respirator Protection requirements under 29 CFR 1910.134. Specific type of respirator will depend of the airborne concentration. Filtering face piece or dust mask is not acceptable for use with this product if TLV filtering levels have been exceeded.

Consult the Safety Data Sheet (SDS) for additional information pertaining to this product.

PRO PASTE RESIN



Commercial Product Data Sheet

Mass and Volume Data for Pro Catalyst Liquid

Pro Catalyst Liquid - net contents per unit			
2.5 kilograms	2.25 liters	2250 milliliters	10 cups

Product	Density (kg per liter)	Liquid Measure (liters per kg)	Liquid Measure (milliliters per kg)
Pro Catalyst Liquid	1.1 kilograms per liter	0.91 liters per kilogram	910 milliliters per kilogram

Pro Catalyst <u>Liquid</u> Mixing Chart Pro Paste Resin						
Resin Quantity	Ambient Temperature 77°F to 95°F (25°C to 35°C)		Ambient Temperature 41°F to 77°F (5°C to 25°C)		Ambient Temperature 32°F to 41°F (0°C to 5°C)	
	Tablespoons	Cups	Tablespoons	Cups	Tablespoons	Cups
1 kg (0.72 liter)	2	n/a	4	n/a	6	n/a
Substrate temperature range for application of Pro Paste Resin is 32°F to 122°F (0°C to 50°C)						

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at www.Siplast.com.