

Product Description

Pro Thixo is a liquid additive that increases the viscosity of Terapro Waterproofing Base Resin, Parapro Roof Membrane Resin, Terapro VTS Resin, and Pro Color Finish Resin.

Product Uses

Pro Thixo is added to the resins to impart thixotropic properties, allowing application on sloped surfaces without slumping or sliding.

Color

Clear.

Packaging

One-liter metal resealable container.

Addition Rate

Pro Thixo is added to resins until the desired viscosity is achieved (resistance to flow). The amount of Pro Thixo added to a resin component should never exceed 1% (by weight).

Mixing

Add Pro Thixo to Terapro Base Resin, Parapro Roof Membrane Resin, Terapro VTS Resin, or Pro Color Finish a minimum of 30 minutes before catalyzation of the resin. Mix thoroughly and replace the resin container lid. After 30 minutes, use the resin in accordance with the Terapro Waterproofing, Terapro VTS, or Parapro Roof Membrane Installer's Guides.

COMMERCIAL PRODUCT INFORMATION

Unit: 1-liter can

Packaging: 1-liter resealable metal container

Handling

Avoid skin and eye contact and breathing fumes. Do not eat, drink, or smoke in area of use.

Storage

The shelf life of Pro Thixo is 12 months from ship date. Store unopened in cool, dry, well-ventilated area away from heat, direct sunlight, oxidizing agents, strong acids, and alkali. Keep away from open flame or any ignition source.

Rev 7/2019

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at www.Siplast.com.

PRO THIXO

PARAPRO ROOF RESIN TERAPRO BASE RESIN				
PRO THIXO RATIOS @ 1/2% BY WEIGHT				
Volume (liters)	Tbsp Thixo		Mass (kg)	Tbsp Thixo
1	0.4		1	0.3
2	0.8		5	1.5
3	1.2		10	3.0
5	1.9		20	6.0
10	3.9			
20	7.8			
1 liter Pro Thixo = 67.5 tablespoons				
1 tablespoon = 0.0167 kg (16.7 grams)				

PARAPRO ROOF RESIN TERAPRO BASE RESIN				
PRO THIXO RATIOS @ 1% BY WEIGHT				
Volume (liters)	Tbsp Thixo		Mass (kg)	Tbsp Thixo
1	0.8		1	0.6
2	1.6		5	3.0
3	2.3		10	6.0
5	3.9		20	12.0
10	7.8			
20	15.5			
1 liter Pro Thixo = 67.5 tablespoons				
1 tablespoon = 0.0167 kg (16.7 grams)				

PRO COLOR FINISH				
PRO THIXO RATIOS @ 1/2% BY WEIGHT				
Volume (liters)	Tbsp Thixo		Mass (kg)	Tbsp Thixo
1	0.3		1	0.3
2	0.6		2	0.6
3	0.9		3	0.9
5	1.5		5	1.5
10	3.0		10	3.0
20	6.0		20	6.0
1 liter Pro Thixo = 67.5 tablespoons				
1 tablespoon = 0.0167 kg (16.7 grams)				

PRO COLOR FINISH				
PRO THIXO RATIOS @ 1% BY WEIGHT				
Volume (liters)	Tbsp Thixo		Mass (kg)	Tbsp Thixo
1	0.6		1	0.6
2	1.2		2	1.2
3	1.8		3	1.8
5	3.0		5	3.0
10	6.0		10	6.0
20	12.0		20	12.0
1 liter Pro Thixo = 67.5 tablespoons				
1 tablespoon = 0.0167 kg (16.7 grams)				

VTS RESIN				
PRO THIXO RATIOS @ 1/2% BY WEIGHT				
Volume (liters)	Tbsp Thixo		Mass (kg)	Tbsp Thixo
1	0.3		1	0.3
2	0.6		2	0.6
3	0.9		3	0.9
5	1.5		5	1.5
10	3.0		10	3.0
1 liter Pro Thixo = 67.5 tablespoons				
1 tablespoon = 0.0167 kg (16.7 grams)				