

PRO PRIMER E

Commercial Product Data Sheet



Pro Primer E is a two component, moisture vapor retarder epoxy primer for use over qualified/approved concrete substrates prior to application of Parapro, Terapro, Terapro VTS & Terapro PUR systems. Pro Primer E is a part of ASTM C957 approved systems.

Contact Siplast for specific information on specified approved product uses.

USES: PMMA ACCESSORY

PRODUCT INFORMATION

	Values / Units	Test Method
Mix Ratio by Volume	2:1	N/A
Pot Life @ 68°F (20°C)	15 minutes	ISO 9514
Tack Free Time @ 68°F (20°C)	2 hours, 50 minutes	ASTM D1640
Adhesion to Concrete	>150 psi	ASTM D7234
Recoat Window	18 hours	
VOC	< 5 g/L (after mixing)	

*Ambient and substrate temperatures affect the application of Terapro PUR Deck Coating Systems. Refer to Installation Guide for ambient and substrate temperature guidelines and restrictions.

Application

Refer to the applicable Siplast Technical or Installers Guide for detailed application information, including application/coverage rates. A & B components must be properly mixed before use.



Storage and Handling

All Siplast priming products should be stored on a clean, flat surface. Do not store containers directly on ground. Always store on pallets or otherwise elevated. Do not open containers until ready to use. Do NOT mix partial pails. Care should be taken that containers are not dropped and container seals are not broken prior to use. All roofing products should be stored in a dry place out of direct exposure to the elements and kept away from excessive heat, fire, or open flames. Standard shelf life is 12 months reduced when stored at temperatures 65°F - 90°F at (18°C - 32°F) 50% Relative Humidity.

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

Packaging

Primary Packaging:
Weight Per Kit: 27.2 lb (12 kg)
Part A Pail: 2 Gal (7.5 L)

Part B Pail: 1 Gal (3.8 L)