


USES:
PA-750 REINFORCEMENT

Roll Length	Min: 750 ft (250 yd)
Roll Width	Avg: 36 in (0.9 m)
Diameter	15 in (0.4 m)

FABRIC PROPERTIES

Property	Value/Unit	Test Method
Sheet Grab Tensile (MD)	29 lb (129 N)	ASTM D4632
Sheet Trapezoid Tear (MD)	5.9 lb (26 N)	ASTM D1117
Unit Weight	1.35 oz/yd ² (46 gsm)	ASTM D3776
Thickness	10.4 mils (0.26 microns)	ASTM D1777

The physical and chemical properties are typical average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations.

PA-750® REINFORCING FABRIC

Commercial Product Data Sheet

PA-750® Reinforcing Fabric is a spunbonded polyester fiber fabric reinforcement designed specifically for use with the PA-750 Hot-Applied Rubberized Waterproofing System. It is not intended to be used at drains, expansion joints or as an exposed flashing.

Contact Siplast for information on approved product uses.

PRODUCT INFORMATION

Application

Refer to the applicable Siplast Technical Guide for detailed application information.

Storage and Handling

All Siplast roll roofing products should be stored on end on a clean flat surface. Rolls should not be dropped on ends or edges or stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing products should be stored in a dry place out of direct exposure to the elements and should not be double stacked. Material should be handled so that it remains dry prior to and during installation.

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

Packaging

Rolls Per Pallet: 38
Weight Per Roll: 64 lb (20 kg)