



PARASOLO® TPO SBA BONDING ADHESIVE

Commercial Product Data Sheet

Parasolo® TPO SBA Bonding Adhesive is a solvent-based, contact-type bonding adhesive specifically designed for bonding Parasolo TPX single-ply roofing membranes and flashings to approved substrates. Parasolo TPO SBA Bonding Adhesive is produced using a fast drying solvent that provides high initial tack and is applied by brush or roller.

Contact Siplast for information on approved product uses.

USES:
TPO MEMBRANE ADHESIVE
TPO FLASHING ADHESIVE

Color	Yellow
Base	Synthetic Polymer
Solvent	Hydrocarbon Blend
Solid Content	25% (± 2.5%)
Flash Point	0°F (-17.8°C)
VOC	611 g/L
Weight	7.4 lb/gal (0.88 kg/L)
Viscosity	2,3000 – 2,700 cps
Shelf Life	12 months (unopened)
Open Time	Up to 60 minutes
Dry Time*	5-15 minutes
Coverage**	50-70 ft ² /gal (1.22-1.72 m ² /L)

*Dry times are approximate and are affected by temperature, wind, and humidity.

**Substrate porosity texture and ambient conditions may affect coverage rates.

PRODUCT INFORMATION

Application

Refer to the applicable Siplast Technical Guide and applicable Siplast details for information on the application of Parasolo TPX membranes with Parasolo TPO SBA Bonding Adhesive.



Storage and Handling

Store material in a clean and well-ventilated area at 40°F – 90°F (4°C – 32.2°C). Storage for extended periods outside this temperature range may shorten shelf life. Keep containers covered when not in use.

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

Packaging

Primary Packaging: 5-gal (18.93 L) metal pails
Pails Per Pallet: 45
Weight: 37 lbs (16.78 kg)

Listings, Approvals, & Certifications



Classified by UL in accordance with ANSI/UL 790. Refer to UL Product iQ for specific assemblies.
FM Approved: Refer to RoofNav.com for specific assemblies.