



**USES:
FINISH PLY
FLASHING SHEET**

Standards	ASTM D6164 Type I, Grade G; CSA A123.23-15 Type B, Grade 1
Roll Length (nominal)	32.6 ft (10 m)
Roll Width (nominal)	39.4 in (1.0 m)
Coverage Per Roll (Typical with 3" Side & End Laps)	0.986 Squares (98.6 ft ²) (9.2 m ²)
Coverage Weight Per Square (nominal)	105.1 lb (5.1 kg/m ²)
Selvage Width (nominal)	3 in (75 mm) Line Color: White
Top Surfacing	Roofing Granules
Back Surfacing	Polyolefin Burn-off Film
Granule Colors	White A-720, White I-720, Bright White (BW), Gray A-9, Gray I-760

PARATECH 180 CAP FR TG

Commercial Product Data Sheet

Paratech 180 Cap FR TG is a modified bitumen finish ply of the Paratech two-ply modified bitumen roof system. Designed for use in homogeneous multi-layer modified bitumen roof membrane systems, Paratech 180 Cap FR TG consists of a 180-gram polyester mat impregnated and coated with a styrene-butadiene-styrene (SBS) modified bitumen blend. The top surface is covered with roofing granules and the back surface is coated with an SBS modified bitumen adhesive layer specifically formulated for torch application, is embossed with a grooved pattern, and is surfaced with a polyolefin burn off film. Approved for use as a protection course in the PA-750 Hot Applied Rubberized Asphalt system.

Contact Siplast for information on approved product uses.

PRODUCT INFORMATION

Application

Refer to the Siplast specifications for detailed application information and slope limitations. Paratech 180 Cap FR TG is lapped 3 inches (76 mm) side and end.



Storage and Handling

All Siplast roll roofing products should be stored on end on a clean flat surface. Rolls should not be dropped on ends or edges or stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing products should be stored in a dry place out of direct exposure to the elements and should not be double stacked. Material should be handled so that it remains dry prior to and during installation.

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

Packaging

Roll Weight (Nominal): 103 lb (47 kg)

Max Pallet Weight (Typical): 2820 lbs (1279 kg)

Pallets Per Truckload (Typical): 15

Listings, Approvals, & Certifications



Classified by UL in accordance with ANSI/UL 790. Refer to UL Product iQ for specific assemblies.
FM Approved - Refer to RoofNav.com for specific assemblies.
Meets or Exceeds CSA A123.23.

Current copies of all Siplast Commercial Product Data Sheets & Safety Data Sheets are posted on our website at www.siplast.com
Rev Date 5/2025

U.S. TEST STANDARDS

Property (as Manufactured)	Values / MD	Values / XMD	Test Method
Thickness (average)	157.5 mils (4.0 mm)		ASTM D5147
Peak Load @ 73.4°F (23°C) (average)	85 lbf/in	65 lbf/in	ASTM D5147
Peak Load @ 0°F (-18°C) (average)	115 lbf/in	90 lbf/in	ASTM D5147
Elongation @ Peak Load 73.4°F (23°C) (average)	40%	50%	ASTM D5147
Elongation @ Peak Load 0°F (-18°C) (average)	35%	40%	ASTM D5147
Ultimate Elongation 73.4°F (23°C)	55%	60%	ASTM D5147
Tear Strength (average)	125 lbf	85 lbf	ASTM D5147
Water Absorption (maximum)	1%		ASTM D5147
Low Temperature Flexibility (maximum)	-15°F (-26°C)	-15°F (-26°C)	ASTM D5147
Dimensional Stability (maximum)	<0.5%	<0.5%	ASTM D5147
Compound Stability (minimum)	240°F (116°C)		ASTM D5147
Granule Embedment	1.5 grams per sample Max. avg. loss		ASTM D5147
	2.0 grams per sample Max. individual loss		

CANADIAN TEST STANDARDS

Property (as Manufactured)		CAS A123.23 Requirement	Tested Value			
Thickness – mm (mils)		3.3 (130)	3.7 (145)			
*Selvage Thickness – mm (mils)		2.2 (85)	2.5 (98)			
Mass Per Unit Area – kg/m ² (lbs/100 ft ²)		3.7 (75)	5.1 (105)			
Back Surface Coating Thickness, min. – mm (mils)		1.0 (40)	1.0 (40)			
			Before Heat Conditioning MD/XD		After Heat Conditioning MD/XD	
Strain Energy, min. – kN/m (lbf/in)	@ 23 ± 2°C (73.4 ± 3.6°F)	5.5 (31)	5.5 (31)	5.5 (31)	5.5 (31)	5.5 (31)
	@ -18 ± 2°C (-0.4 ± 3.6°F)	3.0 (17)	3.0 (17)	3.0 (17)	3.0 (17)	3.0 (17)
Peak Load, min. – kN/m (lbf/in)	@ 23 ± 2°C (73.4 ± 3.6°F)	See Tested Value	17.7 (101)	10.0 (57)	17.3 (99)	10.3 (59)
	@ -18 ± 2°C (-0.4 ± 3.6°F)		23.6 (135)	14.2 (81)	21.9 (125)	13.3 (76)
Elongation @ Peak Load, %	@ 23 ± 2°C (73.4 ± 3.6°F)	See Tested Value	45	49	38	40
	@ -18 ± 2°C (-0.4 ± 3.6°F)		38	41	34	33
Ultimate Elongation @ 23 ± 2°C (73.4 ± 3.6°F), %		See Tested Value	46	55	39	41
Dimensional Stability, max., %		1.0	1.0	1.0	1.0	1.0
Low Temperature Flexibility, max. – °C (°F)		-18 (-0.4)	-26 (-15)	-26 (-15)	-26 (-15)	-26 (-15)
Low Temperature Weathered Flexibility, max. – °C (°F)		-12 (10)	-12 (10)	-12 (10)	-12 (10)	-12 (10)
Compound Stability, min. – °C (°F)		102 (215)	116 (240)	116 (240)	116 (240)	116 (240)
Resistance to Puncture		Pass	Pass			
Granule Loss (Grade 1 only), max. – g (oz)		2.0 (0.07)	1.9 (0.07)			

Data is based upon typical product performance and is subject to normal manufacturing and packaging tolerance and variation.

*Measured on the selvage edge excluding the granule surfacing.

SOLAR REFLECTANCE / THERMAL EMITTANCE

Property (as Manufactured)	Values	Test Method
**Solar Reflectance (avg.)	0.74	ASTM C1549
**Thermal Emittance (avg.)	0.91	ASTM C1371
**Solar Reflectance Index (avg.)	92	ASTM E1980

**Only applies to Bright White (BW) granule surfaced rolls.