

PRO PRIMER T RESIN

Commercial Product Data Sheet



Pro Primer T Resin is a multi-component, fast curing, PMMA resin primer for use over approved substrates.

Contact Siplast for specific information on specified approved product uses.

USES: PMMA ACCESSORY

Colors	Translucent
Conditions at Time of Application	Ambient & Substrate Temperatures: 32°F - 95°F (0°C - 35°C)
Typical Set/Cure Times at 68°F (20°C)	Rainproof: 25 minutes Ready for Next Coat: 45 minutes
Pot Life at 68°F (20°C)	< 10 minutes
VOC Content	< 25 g/L (catalyzed) EPA test method 24

PRODUCT INFORMATION

Application

Refer to the applicable Siplast Technical or Installers Guide for detailed application information, including application/coverage rates. Product must be catalyzed before application using Pro Catalyst Liquid. See mixing charts that are supplied with Pro Catalyst products.



Storage and Handling

Store indoors in well-ventilated, cool, dry area away from heat, open fire, ignition sources, direct sunlight, oxidizing agents, strong acids, and strong alkalis. Do not store below 32°F (0°C). Product may auto-polymerize at temperatures greater than 140°F (60°C). Store jobsite materials on pallets in a shaded, well-ventilated area. Standard shelf life is 12 months; shelf life will be reduced when stored at temperatures above 77°F (25°C).

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

Packaging

Packaging: 10 kg (22 lb) resealable metal drums
Units Per Pallet: 48

Listings, Approvals, & Certifications



Classified by UL in accordance with ANSI/UL 790. Refer to UL Product iQ for specific assemblies.