

TERAPRO® VTS RESIN

Commercial Product Data Sheet



Terapro VTS Resin is a multi-component, fast curing, PMMA resin, that when combined with Terapro VTS Quartz Filler and catalyzed, is used as a waterproofing and/or surfacing layer of Terapro and Terapro VTS Systems.

Contact Siplast for specific information on approved product uses.


USES: TERAPRO SYSTEM COMPONENT

Color	Translucent Tan
Condition at Time of Application	Ambient Temperature: 32°F - 95°F (0°C - 35°C) Substrate Temperature: 32°F - 122°F (0°C - 50°C)
Typical Set/Cure Times at 68°F (20°C)	Rainproof: 30 minutes Stress Resistant: 60 minutes Ready for Next Layer: 2 hours
VOC Content	< 25 g/L (catalyzed) EPA test method 24

PRODUCT INFORMATION

Application

Refer to the applicable Siplast Technical or Installers Guide for detailed application information, including application/coverage rates. Product must be mixed with Terapro VTS Filler and catalyzed with Pro Catalyst Liquid before use. See mixing charts that are supplied with Pro Catalyst products.



Storage and Handling

Store indoors in well-ventilated, cool, dry area away from heat, open fire, ignition sources, direct sunlight, oxidizing agents, strong acids, and strong alkalis. Do not store below 32°F (0°C). Product may auto-polymerize at temperatures greater than 140°F (60°C). Store jobsite materials on pallets in a shaded, well-ventilated area. Standard shelf life is 12 months; shelf life will be reduced when stored at temperatures above 77°F (25°C).

See product packaging and the Safety Data Sheet for specific information on the safe handling of this product.

Packaging

Packaging: 10 kg (22 lb) resealable metal drums
Units Per Pallet: 48

Listings, Approvals, & Certifications



Classified by UL in accordance with ANSI/UL 790. Refer to UL Product iQ for specific assemblies.