
## **TERANAP PLAZA DECK**

## DRAINAGE MAT/PEDESTAL/PAVER SYSTEM



Requirements and recommendations detailed in the Siplast catalog and Siplast long form specifications shall apply in addition to the following recommendations and specifications.

## **Application**

- 1. Prime the entire deck using PA-1125 or PA-917 LS Primer and allow the primer to dry thoroughly.
- 2. Beginning at the low point of the roof, fully torch one ply of Paradiene 20 TG to the primed substrate, lapping sides and ends a minimum of 3 inches. Offset end laps a minimum of 3 feet.
- 3. Beginning again at the low point of the roof, fully torch one ply of Teranap to the Paradiene 20 TG surface, lapping sides and ends a minimum of 6 inches. Offset end laps a minimum of 3 feet. Stagger laps between plies.
- 4. Lay one layer of Paradrain Drainage Mat dry over the finished Teranap surface.
- 5. Install the approved pedestal/paver system over the Paradrain Drainage Mat surface according to the paver system manufacturer's specifications and recommendations.

**Note:** Teranap is manufactured in both 1 meter and 2 meter widths. The Teranap weight shown above is a minimum weight for standard 2 meter wide Teranap. Contact Siplast for weights on other Teranap finish plies.

**Caution:** Siplast recommends that all practices pertaining to NRCA CERTA guidelines be followed when torching methods are employed. This includes performing a fire watch following any torch applications. Always have approved fire-extinguishing equipment nearby.

Ref. #: P20-tg Tnap Concrete Drain-mat Paver-ped

Rev. 10.13.11



1000 East Rochelle Boulevard Irving, Texas 75062 (800) 922-8800 FAX (469) 995-2206

